

BISCO® BF-2000 – ULTRA SOFT SILICONE

BISCO® BF-2000 Ultra Soft is a highly compressible silicone foam. The combination of low weight and softness makes this flame retardant foam ideal for transportation, industrial, and electronics applications where low closure force and dust sealing are critical. BISCO Silicones are available in a variety of thickness options and is manufactured in roll form to allow fabricators to easily convert the material to the proper dimensions.

Features and Benefits

- Ultra low softness allows designers to use less force to seal enclosures and still protect their device from the environment.
- High compressibility allows material to conform to variable width gaps, thereby allowing more design flexibility.
- Excellent memory and low stress relaxation reduces maintenance costs associated with gasket failures due to compression set and softening.
- Resistance to ultraviolet light, ozone, extreme temperatures, and flame enables consistent performance in all environments.
- Available through distribution sites throughout North America, Europe and Asia.

Applications

- Vibration isolation in electronic components and transportation vehicles
- Low closure force gaskets within portable electronics such as laptops and LCD screens within aircraft and rail interiors
- Fire retardant thermal insulation

Installation

Available with a pressure-sensitive adhesive on one or two sides to allow easy application to a variety of surfaces.

BISCO® BF-2000		
Property	Test Method	Typical Value
PHYSICAL		
Color		Black
Thickness , mm (inches) Tolerance		3.18 - 12.70 (0.125 - 0.500) See Reverse
Standard Width , mm (inches)		12.7 - 914 (0.500 - 36.0)
Density , kg/m ³ (lb./ft ³)	ASTM D 1056	160 (10.0)
Compression Force Deflection , kPa (psi)	Force measured @ 25% Deflection ASTM D 1056	13.8 (2.5 Max)
Compression Set , Typical	ASTM D 1056 Test D @ 70°C (158°F), 22 hrs	1%
	ASTM D 1056 Test D @ 100°C (212°F), 22 hrs	5%
Tensile Strength , min. kPa (psi)	ASTM D 412	172 (25)
Elongation , % min.	ASTM D 412	80
FLAMMABILITY & OUTGASSING		
Flame Resistance	UL 94	Listed V-0 and HF-1
Flame Spread Index (I_s)	ASTM E 162	<25
Smoke Density (D_s)	ASTM E 662 Tested @ 4.0 minutes	<50
	Tested @ 1.5 minutes	<20
Toxic Gas Emissions Rating	SMP-800C	Pass

The information contained in this Data Sheet is intended to assist you in designing with Rogers' High Performance Foams. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' High Performance Foams for each application. The Rogers logo, Helping power, protect, connect our world, and BISCO are trademarks of Rogers Corporation or one of its subsidiaries. © 2003, 2006, 2009, 2016 Rogers Corporation, All rights reserved. Printed in U.S.A., 0216-PDF, Publication #180-049

BISCO® BF-2000 – ULTRA SOFT SILICONE (continued)

Standard Thickness Tolerance

Standard Thickness			Tolerance (Inches)
Inches		mm	
1/8	0.125	3.18	± 0.025
3/16	0.188	4.76	± 0.030
1/4	0.250	6.35	± 0.040
3/8	0.375	9.53	± 0.060
1/2	0.500	12.70	± 0.060

Width Tolerance (Cellular)

Nominal Width (Inches)	Tolerance (w/o PSA)	Tolerance (with PSA)
$0 < T \leq 3$	± 0.063	± 0.031
$3 < T \leq 8$	± 0.094	± 0.031
$8 < T \leq 12$	± 0.125	± 0.031
$12 < T \leq 18$	± 0.188	± 0.031
$18 < T \leq 26$	± 0.219	± 0.063
$26 < T \leq 36$	± 0.250	± 0.063

Notes:

1. All metric conversions are approximate.
2. Additional technical information is available.
3. BF-2000 is a recently commercialized standard product that was previously recognized and sold under the BISCO EP-2022 product designation. All product features, properties, and formulations have remained intact in commercializing this Engineered Product (EP) to our BISCO Foam (BF) series.

The information contained in this Data Sheet is intended to assist you in designing with Rogers' High Performance Foams. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' High Performance Foams for each application. The Rogers logo, Helping power, protect, connect our world, and BISCO are trademarks of Rogers Corporation or one of its subsidiaries. © 2003, 2006, 2009, 2016 Rogers Corporation, All rights reserved. Printed in U.S.A., 0216-PDF, Publication #180-049